



**Industrial
Oleochemical
Products**

PRODUCT DATA SHEET

317 Chamberlain Road, Jacobs, South Africa, 4026
Tel: +27 (0) 31 461 8680 Fax : +27 (0) 31 461 3743
Website: www.oleo.co.za Email: info@oleo.co.za

OleoProp SA30-L

Disproportionated distilled tall oil

OleoProp SA-30L is a stabilized, disproportionated distilled tall oil of nominally 30 percent rosin content, used as an emulsifier in the emulsion polymerization process for the manufacture of styrene-butadiene rubber.

Physical Properties

Property	Description
Appearance @25 °C	Clear yellow liquid
Rosin content, (%)	28 - 30
Acid value (mgKOH/g)	180 - 185
Fatty acid content, (%)	59 - 62
Unsaponifiables, (%)	10.5 Max.
Abietic acid content, (%)	0.50 Max.

Useful Product Information

CAS Number	68152-92-1
EC Number	268-858-0
HS Code	-
Flash Point, (°C)	205
Cloud Point, (°C)	Approx. 16
Specific gravity, 25/25°C	Approx. 0.95
Solubility	Insoluble in water. Soluble in most organic solvents

Applications


SBR polymerization
emulsifier

Lubricants

Personal Protective Equipment



Always handle OleoProp product in accordance with the safety data sheet (SDS) and proper safety procedures.



OleoProp SA30-L

PRODUCT DATA SHEET

317 Chamberlain Road, Jacobs, South Africa, 4026
Tel: +27 (0) 31 461 8680 Fax : +27 (0) 31 461 3743
Website: www.oleo.co.za Email: info@oleo.co.za

Feature & Benefits

Synthetic rubber manufacturers using emulsion polymerization to produce styrene-butadiene rubber (SBR) optionally choose a twin-pack emulsifier system comprising:

- i) partially hydrogenated tallow fatty acids
 - ii) disproportionated rosin
- or they can use a single-pack pre-mix combination based on tall oil fatty acids and tall oil rosin.

When converted into soap, these stabilized emulsifiers enable the emulsion polymerization reactions to proceed without hindrance.

Product Packaging

Pallet: 186kgs x 4 and plastic shrink wrapped
Bulk loads ~ 23000 tons - ~32000 tons per load

Other SBR Polymerization Emulsifiers

OleoProp SA40-L, OleoProp DR50KS, OleoProp 900



Handling:	Ensure the use of personal protective equipment (see SDS Section 8) Handle and open container with care. Keep away from heat and sources of ignition. The material is combustible but not classified as flammable. Wash thoroughly after handling. Do not eat and drink or smoke while handling this material.
Storage:	Store in original containers and keep containers tightly closed until ready for use. Store in a cool, dry, well-ventilated place. Note that storage under cool conditions may cause separation of saturated fatty acids components which may cause an increase in viscosity and render the product opaque
Incompatible materials:	Tall oil in contact with un-lined mild steel containers or pipes can result in slow corrosion, depending upon the length of exposure, Darkening of the material may also occur.

Disclaimer

The data contained herein is believed to be accurate. However, neither the above named supplier nor of its partners or distributors assumes any legal liability whatsoever for the accuracy or completeness of information contained herein. Users should undertake sufficient verification and testing to determine the suitability for their own purpose of any product or information contained herein.